TEST REPORT

Applicant	:	**Yangjiang Hasen Industrial Co.,Ltd**
Address	:	**NO.8 Building, 6 Alley, Jiangchun Road, Jiangcheng Area, Yangjiang city, Guangdong province, China**
Manufacturer	:	**Yangjiang Hasen Industrial Co.,Ltd**
Address	:	**NO.8 Building, 6 Alley, Jiangchun Road, Jiangcheng Area, Yangjiang city, Guangdong province, China**

Report on the submitted samples said to be:

Sample Name	:	Food Tongs
Model No.	:	BT5308
Age Group Applied in Testing	:	Adult
Date of Sample Received	:	December 17, 2025
Testing Period	:	December 17, 2025 ~ December 22, 2025
Results	:	**Please refer to next page(s).**

Signed for and on behalf of UNT

Billy Xu

SHENZHEN UNT TECHNOLOGY CO., LTD. APPROVED

Unless otherwise stated the results shown in this report refer only to the sample(s) tested. This test report cannot be reproduced, except in full. Without prior written permission of the company.
If the customer has no specific requirements, the simple method will be used by default.

****

TEST REQUEST		CONCLUSION
A.	European Commission Regulation (EC) No 1935/2004 and Council of Europe Resolution CM/Res(2020)9 on metals and alloys used in food contact materials and articles	**Pass**

****

Unless otherwise stated the results shown in this report refer only to the sample(s) tested. This test report cannot be reproduced, except in full. Without prior written permission of the company.

If the customer has no specific requirements, the simple method will be used by default.

Shenzhen UNT Technology Co., Ltd.

202, Building 3, Yibaolai Industrial City, Qiaotou Community, Fuhai Street, Bao'an District, Shenzhen, Guangdong, China

Tel:0755-23054285 E-mail:unt-ep@unt-lab.com Web:www.unt-lab.com

Tested part(s):

1 Silver metal (clip)

Unless otherwise stated the results shown in this report refer only to the sample(s) tested. This test report cannot be reproduced, except in full. Without prior written permission of the company.

If the customer has no specific requirements, the simple method will be used by default.

Shenzhen UNT Technology Co., Ltd.

202, Building 3, Yibaolai Industrial City, Qiaotou Community, Fuhai Street, Bao'an District, Shenzhen, Guangdong, China

Tel:0755-23054285 E-mail:unt-ep@unt-lab.com Web:www.unt-lab.com

Results:

A. European Commission Regulation (EC) No 1935/2004 and Council of Europe Resolution CM/Res(2020)9 on metals and alloys used in food contact materials and articles

Test Method: With reference to Council of Europe Resolution CM/Res(2020)9

Test Condition: 2 hours at 100℃ in 5 g/L Citric acid.

Test Item(s)	Unit	MDL	Result 1		Limit	
			1st+2nd	3rd	1st+2nd	3rd
Tin (Sn)	mg/kg	1	N.D.	N.D.	700	100
Copper (Cu)	mg/kg	1	N.D.	N.D.	28	4
Iron (Fe)	mg/kg	1	N.D.	N.D.	280	40
Manganese (Mn)	mg/kg	0.1	N.D.	N.D.	12.6	1.8
Zinc (Zn)	mg/kg	1	N.D.	N.D.	35	5
Aluminum (Al)	mg/kg	1	N.D.	N.D.	35	5
Barium (Ba)	mg/kg	0.1	N.D.	N.D.	8.4	1.2
Titanium (Ti)	mg/kg	1	N.D.	N.D.	-	-
Magnesium (Mg)	mg/kg	1	N.D.	N.D.	-	-
Chromium (Cr)	mg/kg	0.05	N.D.	N.D.	1.75	0.25
Nickel (Ni)	mg/kg	0.05	N.D.	N.D.	0.98	0.14
Lithium (Li)	mg/kg	0.01	N.D.	N.D.	0.336	0.048
Beryllium (Be)	mg/kg	0.001	N.D.	N.D.	0.07	0.01
Vanadium (V)	mg/kg	0.001	N.D.	N.D.	0.07	0.01
Cobalt (Co)	mg/kg	0.001	N.D.	N.D.	0.14	0.02
Molybdenum (Mo)	mg/kg	0.01	N.D.	N.D.	0.84	0.12
Silver (Ag)	mg/kg	0.01	N.D.	N.D.	0.56	0.08
Antimony (Sb)	mg/kg	0.01	N.D.	N.D.	0.28	0.04
Lead (Pb)	mg/kg	0.001	N.D.	N.D.	0.07	0.01
Arsenic (As)	mg/kg	0.0001	N.D.	N.D.	0.014	0.002
Cadmium (Cd)	mg/kg	0.001	N.D.	N.D.	0.035	0.005
Mercury (Hg)	mg/kg	0.001	N.D.	N.D.	0.021	0.003
Thallium (Tl)	mg/kg	0.0001	N.D.	N.D.	0.0007	0.0001
Conclusion	/	/	**Pass**		/	/

Unless otherwise stated the results shown in this report refer only to the sample(s) tested. This test report cannot be reproduced, except in full. Without prior written permission of the company.

If the customer has no specific requirements, the simple method will be used by default.

Note:

- mg/kg = ppm
- N.D. = Not Detected or less than MDL
- MDL = Method Detection Limit
- "+" = Composite testing
- Tested part(s) was/were specified by client.
- Photo appendix is included

Unless otherwise stated the results shown in this report refer only to the sample(s) tested. This test report cannot be reproduced, except in full. Without prior written permission of the company.


If the customer has no specific requirements, the simple method will be used by default.

Shenzhen UNT Technology Co., Ltd.

202, Building 3, Yibaolai Industrial City, Qiaotou Community, Fuhai Street, Bao'an District, Shenzhen, Guangdong, China

Tel:0755-23054285 E-mail:unt-ep@unt-lab.com Web:www.unt-lab.com

The photo of the sample



UNT authenticate the photo on original report only

Unless otherwise stated the results shown in this report refer only to the sample(s) tested. This test report cannot be reproduced, except in full. Without prior written permission of the company.

If the customer has no specific requirements, the simple method will be used by default.

Statement:

1. This test report is invalid without the signature of the approver and the special seal of the company's report.
2. The copy of the test report is invalid if the "Special Seal for Inspection and Testing" or "Special Seal for testing" or the official seal of the testing unit is not re-stamped.
3. After the test report is altered, the test report is invalid.
4. If there is any objection to the test report, please submit written comments to the laboratory within 15 days from the date of receipt of the report.
5. This test is only responsible for samples provided by customers.
6. This report shall not be reproduced in whole or in part without the written authorization of the Company.
7. The laboratory is not responsible for sampling, all samples are provided by customers.
8. The test results in this test report are only related to the samples provided by the customer.

*** End of Report ***

Unless otherwise stated the results shown in this report refer only to the sample(s) tested. This test report cannot be reproduced, except in full. Without prior written permission of the company.

If the customer has no specific requirements, the simple method will be used by default.